

# Technical Data Sheet



## SAGA Premium Bake & Cook 41 WS

Greaseproof paper made of bleached pulp and surface sized with silicone, wet strong.

Excellent release towards all baking goods. Designed for processes in institutional kitchens, e.g. Cook & Chill, Cook & Hold, but also for all baking processes, steaming, contact grilling, frying etc. Can stay in GN Liner together with pre-prepared meals up to 5 days.

## Food Contact, Quality and Environment

Production mill is certificated according ISO 9001, ISO 14001, ISO 50001, OHSAS 18001, BRC-CP, IFS-HPC and PEFC/FSC (COC standards).

Products fulfil Kosher, Halal, Nordic Swan and the requirements of Code of Federal Regulations, Food and Drugs (FDA), 21 CFR CH 1 and the requirements of German Recommendation XXXVI and XXXVI/2 also Regulation No 1935/2004, Décret No 92-631 and compostability according to EN 13432.

Property	Unit	Test method	Typical values
Grammage	g/m <sup>2</sup>	ISO 536	41.0 (39.0 – 43.0)
Moisture	%	ISO 287	5.0 (4.0 – 6.0)
ISO-Brightness	%	ISO 2470-1	75
Tensile Strength MD	kN/m	ISO 1924-3	4.1
Tensile Strength CD	kN/m	ISO 1924-3	1.9
Bursting Strength	kPa	ISO 2758	120
Bursting Strength 245°C/6min.	kPa	ISO 2758	105
Cobb60	g/m <sup>2</sup>	EN 20535	11
Greaseproofness (Helga)	ml/h	Permeability Analyser	< 1300
Roll cake 8min/225°C	g/m <sup>2</sup>	Metsä Tissue	11 – 30
Pudding test 200°C/13min.	√	Metsä Tissue	√
Pretzel 4% NaOH 200°C/15min.	√	Metsä Tissue	√
Crispbread 180°C/30min.	√	Metsä Tissue	√